

# Line of Symmetry

## FACT SHEET

Tiny ribbed lines are the embodiment of Line of Symmetry creating a very structured and proper look on the wall. This structure can be softened with the use of its companion piece, Symmetry. Symmetry uses groupings of these ribbed lines to create overlapping circles through the use of reflection. Two other companions add to the possibilities with the silk like background texture of Axis, or the small scaled geometric texture of Vertex.

	US UNITS	METRIC UNITS
<b>Total Weight</b>	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
<b>Roll Width</b>	52/54 in.	132/137 cm
<b>Gauge (avg)</b>	0.22 in.	0.56 mm
<b>Fabric</b>	Nonwoven	
<b>Tensile (Minimum)</b>	50 x 55 lb <sub>f</sub>	222 x 245 N
<b>Tear (Minimum)</b>	25 x 25 lb <sub>f</sub>	111 x 111 N
<b>Federal Spec</b>	CCC-W-408D, Type II	
<b>WA Spec</b>	WA-101, Type II	
<b>ASTM F-793</b>	Category V, Type II	
<b>Fire Testing</b>	NFPA 101® Life Safety Code® NFPA 255 (UL723, CAN S102M) Tunnel Test <sup>1</sup> Class A Rating Flame Spread      10 Smoke Developed    5 NFPA 286 Corner Burn Test <sup>2</sup> Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
<b>Indoor Air Quality</b>	California 01350 - Meets emission requirements for schools and offices	
<b>Repeat</b>	Vertical Horizontal Nominal Pattern Width Match Information	N/A N/A 52 in.      132 cm Random Match- Align vertical stripes, Reverse Hang
1 When applied to GRC Board with A-848-B adhesive		2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive

### Available in 9 Colorways

1822-59 Eclipse  
 1822-69 Espresso  
 1822-20 Eternity  
 1822-77 Indigo Night  
 1822-25 Moonlight  
 1822-61 Mystic  
 1822-90 Shadow  
 1822-92 Sterling  
 1822-38 Whisper

Vinyl wallcovering has a multitude of characteristics that allow it to provide an attractive and serviceable wall surface. One of the characteristics of vinyl wallcoverings is very low moisture permeability. Therefore, it is important to assure that there are no deficiencies in the design, construction and maintenance of a building that allows moisture to accumulate in a wall cavity. The use of a vinyl wallcovering in such a deficient circumstance would result in the vinyl wallcovering acting as a vapor barrier and restricting the passage of the moisture and increasing the chance of mold growth. It is recommended that walls be checked with a suitable moisture meter prior to installation and the moisture content should not exceed 4%. Wallcovering should not be installed on a wall until water/moisture incursion has been eliminated. On renovation projects, examine walls that are to receive wallcovering and assure they do not exhibit any mold/mildew. All mold and mildew must be removed and surfaces treated to inhibit future growth. In order to reduce the risk of mold/mildew, Koroseal Interior Products LLC utilized an inhibitor in the wallcovering. The company can also provide a service of microventing the wallcovering whereby more than 25,000 micro-holes /ft<sup>2</sup> are fused through the vinyl thereby making it permeable.