Arte® for Koroseal®

3875 Embassy Parkway Fairlawn, OH 44333

855.753.5474

koroseal.com



Concord is an edgy take on the folded linen textures of the past. The vertical linen emboss is slashed with hard edged lines to give the pattern a dramatic finish.

		US UNITS	METRIC UNITS	
Total Weight		20 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM	
Roll Width		52" – 54"	132 - 137cm	
Gauge		.022"	0.56 mm	
Fabric		Woven		
Tensile (Minimum)		$50 \times 55 lb_f$	222 x 245 N	
Tear (Minimum)		25 x 25 lb _f	111 x 111 N	
Federal Spec		CCC-W-408A, Type II		
WA Spec		WA 101 - 2011, Type II		
ASTM F-793		Category V, Type II		
Fire Testing		NFPA 101 [®] Life Safety Code [®] ASTM E-84 Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed & Flashover		
CE Certification		EU classification in accordance with EN15102:2007 + A1:2011 Fire Behavior – B Smoke Production – s ² Flame Droplets – d ⁰		
Repeat	Vertical Horizontal Nominal Pattern Width Match Information	N/A N/A 51" Reverse Hang		
1 When applied to GRC Board with A-848-B adhesive		2 When applied to 5/8" type-X gypsum board with A-848-B adhesive		
т жиен арриес	TO ONC BOARD WITH A-040-D AUTIESTVE	2 which applied to 5/6 type-X	gypsuiii boaid with A-040-B auliesive	

Available in 8 Colorways

67240	67244
67241	*67246
67242	*67250
*67243	67251

^{*} These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the material along with excessive scrubbing.

Arte®

3875 Embassy Parkway Fairlawn, OH 44333

855.753.5474 koroseal.com

Concord (Mylars) FACT SHEET

Concord is an edgy take on the folded linen textures of the past. The vertical linen emboss is slashed with hard edged lines to give the pattern a dramatic finish.

		US UNITS	METRIC UNITS	
Total Weight		20 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM	
Roll Width		52" – 54"	132 - 137cm	
Gauge		.020"	0.56 mm	
Fabric		Non-woven		
Tensile (Minimum)		$50 \times 55 \text{ lb}_{\text{f}}$	222 x 245 N	
Tear (Minimum)		$25 \times 25 \text{ lb}_{\text{f}}$	111 x 111 N	
Federal Spec		CCC-W-408A, Type II		
WA Spec		WA 101 - 2011, Type II		
ASTM F-793		Category V, Type II		
Fire Testing		NFPA 101 [®] Life Safety Code [®] NFPA255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover		
CE Certification		EU Classification in accordance with EN15102:2007 + A1:2011 Fire Behavior – B Smoke Production – s^1 Flame Droplets – d^0		
Repeat	Vertical Horizontal Nominal Pattern Width Match Information	N/A N/A 51" Reverse Hang		
1 When applied to GRC Board with A-848-B adhesive 2 When applied to 5/8" type-X gypsum board with A-848-B adhesive				

Available in 4 Colorways

67245

67247

67248

67249

These Mylar Wallcoverings require special handling and have specific installation instructions. Please refer to Koroseal's Mylar Wallcovering Installation Instructions for further details.

57-18-4020 - 4/2017