

# KOROGARD SURFACE BURNING TEST RESULTS



**Korogard 500** Protective Wallcovering is intended for application with the specified adhesive in accordance with instructions accompanying the product.

## Applied to Inorganic Reinforced Cement Board

	.050 IN. (1.27mm.) or less*	.060 in. (1.52 mm.) or less*	.093 in. (2.36 mm.) or less*
<b>Flame Spread</b>	25	20	35
<b>Smoke Developed</b>	40	350	350-450
	No Ch. 028 in. (.71 mm.) ++		
<b>Flame Spread</b>	20		
<b>Smoke Developed</b>	140		

**Korogard 600** Protective Wallcovering is intended for application with the specified adhesive in accordance with instructions accompanying the product.

## Applied to Inorganic Reinforced Cement Board

	.060 in. (1.52 mm.) or Less*	.080 in. (2.03 mm.) or Less*
<b>Flame Spread</b>	20	20
<b>Smoke Developed</b>	130-174	250

\* Applied with 3M™ Fastbond™ Contact Adhesive 30NF at an application rate of 130 sq. ft. per gallon.

++ Applied with XT2000+™ Mastic adhesive at an application rate of 120 sq. ft. per gallon or Spray-Lock® FRP adhesive at an application rate of 70 sq. ft. per can.