

In the past tapestries were used as a way of recording the history, lives and heritage of past generations. Our Lineage pattern combines horizontal and vertical lines over a pearlized file ground creating the look of a woven or a new generation of tapestry for today.

	US UNITS	METRIC UNITS
Total Weight	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
Roll Width	52/54 in.	132/137 cm
Gauge (avg)	0.22 in.	0.56 mm
Fabric	Woven	
Tensile (Minimum)	50 x 55 lb _f	222 x 245 N
Tear (Minimum)	25 x 25 lb _f	111 x 111 N
Federal Spec	CCC-W-408D, Type II	
WA Spec	WA-101, Type II	
ASTM F-793	Category V, Type II	
Fire Testing	NFPA 101® Life Safety Code® NFPA 255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
Indoor Air Quality	California 01350 - Meets emission requirements for schools and offices	
Repeat	Vertical Horizontal Nominal Pattern Width Match Information	N/A N/A 51 in. Random Match, Non-Reverse Hang 130 cm
1 When applied to GRC Board with A-848-B adhesive 2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive		

Available in 16 Colorways

9521-52 Ancestry	9521-48 Journey
9521-66 Clan	9521-36 Kin
9521-69 Colony	9521-28 Legacy
9521-98 Descent	9521-10 Origin
9521-42 Family Tree	9521-35 Pedigree
9521-30 Generation*	9521-77 Progeny
9521-22 Heir	9521-59 Succession
9521-29 Heritage	9521-80 Tribe

*** These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the material along with excessive scrubbing.**

Vinyl wallcovering has a multitude of characteristics that allow it to provide an attractive and serviceable wall surface. One of the characteristics of vinyl wallcoverings is very low moisture permeability. Therefore, it is important to assure that there are no deficiencies in the design, construction and maintenance of a building that allows moisture to accumulate in a wall cavity. The use of a vinyl wallcovering in such a deficient circumstance would result in the vinyl wallcovering acting as a vapor barrier and restricting the passage of the moisture and increasing the chance of mold growth. It is recommended that walls be checked with a suitable moisture meter prior to installation and the moisture content should not exceed 4%. Wallcovering should not be installed on a wall until water/moisture incursion has been eliminated. On renovation projects, examine walls that are to receive wallcovering and assure they do not exhibit any mold/mildew. All mold and mildew must be removed and surfaces treated to inhibit future growth. In order to reduce the risk of mold/mildew, RJF International Corporation utilized an inhibitor in the wallcovering. The company can also provide a service of microventing the wallcovering whereby more than 25,000 micro-holes /ft2 are fused through the vinyl thereby making it permeable.