

Seeing two waves cross at oblique angles due to converging currents or wind direction shifts is not frequently observed in nature. We've taken this unique occurrence and turned it into a unique wallcovering where vertically printed waves cross with horizontal embossed waves.

	US UNITS	METRIC UNITS
<b>Total Weight</b>	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
<b>Roll Width</b>	53/55 in.	135/140 cm
<b>Gauge (avg)</b>	0.024 in.	0.61 mm
<b>Fabric</b>	Osnaburg	
<b>Tensile (Minimum)</b>	50 x 55 lb <sub>f</sub>	222 x 245 N
<b>Tear (Minimum)</b>	25 x 25 lb <sub>f</sub>	
<b>Federal Spec</b>	CCC-W-408D, Type II	
<b>WA Spec</b>	WA-101, Type II	
<b>ASTM F-793</b>	Category V, Type II	
<b>Fire Testing</b>	NFPA 101® Life Safety Code® NFPA 255 (ASTM E-84, CAN S102M) Tunnel Test <sup>1</sup> Class A Rating Flame Spread 10 Smoke Developed 5 NFPA 286 Corner Burn Test <sup>2</sup> Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
<b>Indoor Air Quality</b>	California 01350- Meets emission requirements for schools and offices	
<b>Repeat</b>	Vertical 9 in. Horizontal 13.25 in. (with half drop at 6.625 in.) Nominal Pattern Width 52 in. Match Information Random Match maintaining spacing, Reverse Hang	22.86 cm 33.66 cm 132 cm

<sup>1</sup> When applied to GRC Board with A-848-B adhesive      <sup>2</sup> When applied to 5/8" Type-X gypsum board with A-848-B adhesive

**Available in 18 Colorways**

- |                     |                      |                   |
|---------------------|----------------------|-------------------|
| CW21-79 Abyss*      | CW21-29 Sand Dollar* | CW21-60 Starfish* |
| CW21-54 Beach Sand* | CW21-32 Sea Horse    | CW21-55 Walrus*   |
| CW21-82 Caribbean*  | CW21-90 Sealskin*    |                   |
| CW21-39 Clamshell*  | CW21-38 Sea Otter    |                   |
| CW21-66 Coral Reef* | CW21-59 Sea Urchin*  |                   |
| CW21-51 Dolphin     | CW21-88 Seaweed*     |                   |
| CW21-84 Kelp*       | CW21-91 Sharkskin*   |                   |
| CW21-70 Manatee*    | CW21-77 Squid Ink*   |                   |

**\* These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the material along with excessive scrubbing.**

Vinyl wallcovering has a multitude of characteristics that allow it to provide an attractive and serviceable wall surface. One of the characteristics of vinyl wallcoverings is very low moisture permeability. Therefore, it is important to assure that there are no deficiencies in the design, construction and maintenance of a building that allows moisture to accumulate in a wall cavity. The use of a vinyl wallcovering in such a deficient circumstance would result in the vinyl wallcovering acting as a vapor barrier and restricting the passage of the moisture and increasing the chance of mold growth. It is recommended that walls be checked with a suitable moisture meter prior to installation and the moisture content should not exceed 4%. Wallcovering should not be installed on a wall until water/moisture incursion has been eliminated. On renovation projects, examine walls that are to receive wallcovering and assure they do not exhibit any mold/mildew. All mold and mildew must be removed and surfaces treated to inhibit future growth. In order to reduce the risk of mold/mildew, Koroseal Interior Products, LLC utilized an inhibitor in the wallcovering. The company can also provide a service of microventing the wallcovering whereby more than 25,000 micro-holes /ft2 are fused through the vinyl thereby making it permeable.