Koroseal[®] DEALS

3875 Embassy Parkway Fairlawn, OH 44333

855.753.5474 koroseal.com

DEALS 1001 FACT SHEET

	US UNITS	METRIC UNITS
Total Weight	20.0 oz. PLY 13.3 oz. PSY	618 g PLM 451 g PSM
Roll Width	52/54 in.	132/137 cm.
Gauge	.025 in.	0.635 mm.
Fabric	Non-Woven	
Tensile (Minimum)	50 x 55 lb _f	222 x 245 N
Tear (Minimum)	25 x 25 lb _f	111 x 111 N
Federal Spec.	CCC-W-408D, Type II	
WA Spec.	WA-101, Type II	
ASTM F-793	Category V, Type II	
Fire Testing	NFPA 101 [®] Life Safety Code [®] NFPA 255 (ASTM E-84, CAN S102M)) Tunnel Test ¹ Class A Rating Flame Spread - 10 Smoke Developed - 5 NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover	
CE Certification	EU classification in accordance with EN 15102:2007 + A1:2011	
Indoor Air Quality	California 01350 - Meets emission requirements for schools and offices	
RepeatVertical Horizontal Nominal Information Match Information	N/A N/A 51'' Random Match, Reverse Hang	
1 When applied to GRC board with A-848-B adhesive	en applied to GRC board with A-848-B adhesive 2 When applied to 5/8" Type-X-Gypsum board with A-848-B adhesive	