

		US UNITS	METRIC UNITS
Total Weight		24.0 oz PLY 16.0 oz PSY	814 g PLM 542 g PSM
Roll Width		53/55 in.	134/140 cm
Gauge		26 Mils	0.66 mm
Fabric		Woven	
Tensile (Minimum)		50 x 55 lb _f	222 x 245 N
Tear (Minimum)		25 x 25	
Federal Spec		CCC-W-408A, Type II	
WA Spec		WA -101, Type II	
Fire Testing		NFPA 101® Life Safety Code® NFPA255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover	
Repeat	Vertical: Horizontal: Nominal Pattern Width: Match Information:	N/A N/A 51 in. Random Match, Non-Reverse Hang	130 cm
¹ When applied to GRC Board with A-848-B adhesive		² When applied to 5/8" type-X gypsum board with A-848-B adhesive	

	US UNITS	METRIC UNITS
Total Weight	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
Roll Width	53/55 in.	134 / 140 cm
Gauge (avg)	0.22 in.	.56mm
Fabric	Non-Woven	
Tensile (Minimum)	50 x 55 lb _f	222 x 245 N
Tear (Minimum)	25 x 25 lb _f	111 x 111 N
Federal Spec	CCC-W-408D, Type II	
WA Spec	WA-101, Type II	
ASTM F-793	Category V, Type II	
Fire Testing	NFPA 101® Life Safety Code® NFPA 255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating Flame Spread 10 Smoke Developed 5 NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
Indoor Air Quality	California 01350 - Meets emission requirements for schools and offices	
Repeat	Vertical: N/A Horizontal: N/A Nominal Pattern Width: 52 in. Match Information: Random Match, Reverse Hang	132 cm
1 When applied to GRC Board with A-848-B adhesive		2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive

		US UNITS	METRIC UNITS
Total Weight		21.0 oz PLY 14.0 oz PSY	651 g PLM 475 g PSM
Roll Width		52/54 in.	132/137 cm
Gauge		21 Mils	0.53 mm
Fabric		Non-Woven	
Tensile (Minimum)		50 x 55 lb _f	222 x 245 N
Tear (Minimum)		25 x 25 lb _f	
Federal Spec		CCC-W-408A, Type II	
WA Spec		WA-101, Type II	
Fire Testing		NFPA 101® Life Safety Code® NFPA255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover	
Repeat	Vertical: Horizontal: Match Information:	18" N/A Reverse, Match Horizontal Lines	
1 When applied to GRC Board with A-848-B adhesive		2 When applied to 5/8" type-X gypsum board with A-848-B adhesive	

	US UNITS	METRIC UNITS
Total Weight	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
Roll Width	52/54 in.	132/137 cm
Gauge (avg)	0.24 in.	0.61 mm
Fabric	Non-Woven	
Tensile (Minimum)	50 x 55 lb _f	222 x 245 N
Tear (Minimum)	25 x 25 lb _f	111 x 111 N
Federal Spec	CCC-W-408D, Type II	
WA Spec	WA-101, Type II	
ASTM F-793	Category V, Type II	
Fire Testing	NFPA 101® Life Safety Code® NFPA 255 (ASTM E-84, CAN S102M) Tunnel Test ¹ Class A Rating Flame Spread 10 Smoke Developed 5 NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008 California 01350 - Meets emission requirements for schools and offices	
Indoor Air Quality		
Repeat	Vertical: N/A Horizontal: N/A Nominal Pattern Width: 51 in. Match Information: Random Match, Reverse Hang	130 cm
1 When applied to GRC Board with A-848-B adhesive 2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive		

	US UNITS	METRIC UNITS
Total Weight	21.0 oz PLY 14.0 oz PSY	651 g PLM 475 g PSM
Roll Width	52/54 in.	132/137 cm
Gauge	20 Mils	0.51 mm
Fabric	Woven	
Tensile (Minimum)	50 x 50 lb _f	222 x 222 N
Tear (Minimum)	25 x 25 lb _f	
Federal Spec	CCC-W-408A, Type II	
WA Spec	WA-101, Type II	
Fire Testing	NFPA 101® Life Safety Code® NFPA255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover	
Repeat	Vertical: Horizontal: Match Information:	N/A N/A Reverse, Random Match
1 When applied to GRC Board with A-848-B adhesive		2 When applied to 5/8" type-X gypsum board with A-848-B adhesive

Decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the wallcoverings as does excessive scrubbing.

	US UNITS	METRIC UNITS
Total Weight	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
Roll Width Gauge	52/54 in.	132/137 cm
(avg) Fabric	0.22 in.	0.56 mm
Tensile (Minimum)	Woven	
Tear (Minimum)	50 x 55 lb _f	222 x 245 N
Federal Spec WA	25 x 25 lb _f	111 x 111 N
Spec	CCC-W-408D, Type	
ASTM F-793 Fire	II WA-101, Type II	
Testing	Category V, Type II NFPA 101® Life Safety Code® NFPA 255 (UL723, CAN S102M) Tunnel Test ¹ Class A Rating NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
Indoor Air Quality	California 01350 - Meets emission requirements for schools and offices	
Repeat	Vertical Horizontal Nominal Pattern Width Match Information	N/A N/A 51 in. Random Match, Non-Reverse Hang
1 When applied to GRC Board with A-848-B adhesive	2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive	130 cm