



Total Weight	20 oz. ply (618 g. plm.)	Roll Size	30/60/100 yard bolt
Roll Width	52-54 in. (132-137 cm.)	Core Diameter	3 in.
Backing	Woven	Weight	18.3 oz per lineal yard
Tensile (Minimum)	50 x 55 lb _f (222 x 245 N)	Thickness	Varies depending on texture
Tear (Minimum)	25 x 25 lb _f (111 x 111 N)	WA Spec.	WA-101, Type II
Federal Spec.	CCC-W-408D, Type II	ASTM F-793	Category V, Type II

NFPA 101® Life Safety Code®

NFPA 255 (ASTM E-84, CAN \$102M) Tunnel Test¹

- Class A Rating

- Flame Spread - 10

Fire Testing - Smoke Developed - 5

NFPA 286 Corner Burn Test²

- Meets requirements for Flame Spread, Smoke Developed, & Flashover

1 When applied to GRC board with A-848-B adhesive 2 When applied to 5/8" Type-X-Gypsum board with A-848-B adhesive

CE Certification EU classification in accordance with EN 15102:2007 + A1:2011

Indoor Air Quality California 01350 - Meets emission requirements for schools and offices