

TEST RESULTS SURFACE BURNING CHARACTERISTICS

Korogard 500 Protective Wallcovering is intended for application with the specified adhesive in accordance with instructions accompanying the product.

Applied to Inorganic Reinforced Cement Board

	.050 in. (1.27 mm.) or Less*	.060 in. (1.52 mm.) or Less*	.093 in. (2.36 mm.) or Less*
Flame Spread	25	20	35
Smoke Developed	40	350	350-450
	.028 in. (.71 mm.) ++		
Flame Spread	20		
Smoke Developed	140		

Korogard 600 Protective Wallcovering is intended for application with the specified adhesive in accordance with instructions accompanying the product.

Applied to Inorganic Reinforced Cement Board

	.060 in. (1.52 mm.) or Less*	.080 in. (2.03 mm.) or Less*
Flame Spread	20	20
Smoke Developed	130-175	250

* Applied with 3M™ Fastbond™ Contact Adhesive 30NF at an application rate of 130 sq. ft. per gallon.

++ Applied with XT2000+™ Mastic adhesive at an application rate of 120 sq. ft. per gallon or Spray-Lock® FRP adhesive at an application rate of 70 sq. ft. per can.