

A finely tuned silk with rich refined elegance; a true classic.

	US UNITS	METRIC UNITS
<b>Total Weight</b>	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
<b>Roll Width</b>	52/54 in.	132/140 cm
<b>Gauge (avg)</b>	0.021 in.	0.58 mm
<b>Fabric</b>	Osnaburg	
<b>Tensile (Minimum)</b>	50 x 55 lb <sub>f</sub>	222 x 245 N
<b>Tear (Minimum)</b>	25 x 25 lb <sub>f</sub>	111 x 111 N
<b>Federal Spec</b>	CCC-W-408D, Type II	
<b>WA Spec</b>	WA-101, Type II	
<b>ASTM F-793</b>	Category V, Type II	
<b>Fire Testing</b>	NFPA 101® Life Safety Code® NFPA 255 (ASTM E-84, CAN S102M) Tunnel Test <sup>1</sup> Class A Rating Flame Spread 10 Smoke Developed 5 NFPA 286 Corner Burn Test <sup>2</sup> Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
<b>Indoor Air Quality</b>	California 01350 - Meets emission requirements for schools and offices	
<b>Repeat</b>	Vertical N/A Horizontal N/A Nominal Pattern Width 51 in. Match Information Random Match, Reverse Hang	129 cm
1 When applied to GRC Board with A-848-B adhesive		2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive

### Available in 23 Colorways

2R21-38 Anjou*	2R21-71 Miso Ocean	2R21-76 Shadow*
2R21-12 Astana Cream	2R21-41 Misty	2R21-98 Sichuan Grey
2R21-29 Bamboo	2R21-18 Morning Dove	2R21-22 Sisal
2R21-21 Canfu	2R21-10 Nuance*	2R21-79 Tidewater
2R21-62 Crimson	2R21-67 Papaya	2R21-57 Treasure*
2R21-27 Gobi Tan	2R21-04 Pearl	2R21-50 Truffle*
2R21-92 Midnight*	2R21-55 Pewter*	2R21-52 Zinc*
2R21-31 Midori*	2R21-14 Seagull	

\* These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the material along with excessive scrubbing.

Vinyl wallcovering has a multitude of characteristics that allow it to provide an attractive and serviceable wall surface. One of the characteristics of vinyl wallcoverings is very low moisture permeability. Therefore, it is important to assure that there are no deficiencies in the design, construction and maintenance of a building that allows moisture to accumulate in a wall cavity. The use of a vinyl wallcovering in such a deficient circumstance would result in the vinyl wallcovering acting as a vapor barrier and restricting the passage of the moisture and increasing the chance of mold growth. It is recommended that walls be checked with a suitable moisture meter prior to installation and the moisture content should not exceed 4%. Wallcovering should not be installed on a wall until water/moisture incursion has been eliminated. On renovation projects, examine walls that are to receive wallcovering and assure they do not exhibit any mold/mildew. All mold and mildew must be removed and surfaces treated to inhibit future growth. In order to reduce the risk of mold/mildew, RJF International Corporation utilized an inhibitor in the wallcovering. The company can also provide a service of microventing the wallcovering whereby more than 25,000 micro-holes /ft<sup>2</sup> are fused through the vinyl thereby making it permeable.