## Koroseal® DEALS

3875 Embassy Parkway Fairlawn, OH 44333

855.753.5474 koroseal.com

## DEALS 1011 FACT SHEET

		US UNITS	METRIC UNITS
Total Weight		20.0 oz. PLY 13.3 oz. PSY	618 g PLM 451 g PSM
Roll Width		52/54 in.	132/137 cm.
Gauge		.025 in.	0.635 mm.
Fabric		Woven	
Tensile (Minimum)		50 x 55 lb <sub>f</sub>	222 x 245 N
Tear (Minimum)		25 x 25 lb <sub>f</sub>	111 x 111 N
Federal Spec.		CCC-W-408D, Type II	
WA Spec.		WA-101, Type II	
ASTM F-793		Category V, Type II	
Fire Testing		NFPA 101 <sup>®</sup> Life Safety Code <sup>®</sup> NFPA 255 (ASTM E-84, CAN S102M)) Tunnel Test <sup>1</sup> Class A Rating Flame Spread - 10 Smoke Developed - 5 NFPA 286 Corner Burn Test <sup>2</sup> Meets requirements for Flame Spread, Smoke Developed and Flashover	
CE Certification		EU classification in accordance with EN 15102:2007 + A1:2011	
Indoor Air Quality		California 01350 - Meets emission requirements for schools and offices	
Repeat	Vertical Horizontal Nominal Information Match Information	N/A N/A 51" Random Match, Reverse Hang	
1 When applied to GRC board with A-848-B adhesive		2 When applied to 5/8" Type-X-Gypsum board with A-848-B adhesive	