

Courtyard’s clean graceful lines create a soft geometric pattern that is quaint in the small scale and creates more of a geometric texture on the wall. Its companion, Promenade, offers the same design in a large scale making a bold statement in sophisticated rich colors or a more relaxed one in lighter neutral palettes of pearl essence.

	US UNITS	METRIC UNITS
<b>Total Weight</b>	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
<b>Roll Width</b>	53/55 in.	134/140 cm
<b>Gauge (avg)</b>	0.022 in.	0.56 mm
<b>Fabric</b>	Nonwoven	
<b>Tensile (Minimum)</b>	50 x 55 lb <sub>f</sub>	222 x 245 N
<b>Tear (Minimum)</b>	25 x 25 lb <sub>f</sub>	111 x 111 N
<b>Federal Spec</b>	CCC-W-408D, Type II	
<b>WA Spec</b>	WA-101, Type II	
<b>ASTM F-793</b>	Category V, Type II	
<b>Fire Testing</b>	NFPA 101® Life Safety Code® NFPA 255 (UL723, CAN S102M) Tunnel Test <sup>1</sup> Class A Rating Flame Spread 10 Smoke Developed 5 NFPA 286 Corner Burn Test <sup>2</sup> Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
<b>Indoor Air Quality</b>	California 01350 - Meets emission requirements for schools and offices	
<b>Repeat</b>	Vertical Horizontal Nominal Pattern Width Match Information	1.0 in. 0.96 in. 52 in. Straight Match, Non-Reverse Hang
	1 When applied to GRC Board with A-848-B adhesive	2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive

**Available in 8 Colorways**

- C522-36 Admiration
- C522-61 Barista
- C522-23 Crush
- C522-92 Curiosity\*
- C522-18 Flirt
- C522-16 Interlude
- C522-50 Serendipity
- C522-11 Timid

\* These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the material along with excessive scrubbing.

Vinyl wallcovering has a multitude of characteristics that allow it to provide an attractive and serviceable wall surface. One of the characteristics of vinyl wallcoverings is very low moisture permeability. Therefore, it is important to assure that there are no deficiencies in the design, construction and maintenance of a building that allows moisture to accumulate in a wall cavity. The use of a vinyl wallcovering in such a deficient circumstance would result in the vinyl wallcovering acting as a vapor barrier and restricting the passage of the moisture and increasing the chance of mold growth. It is recommended that walls be checked with a suitable moisture meter prior to installation and the moisture content should not exceed 4%. Wallcovering should not be installed on a wall until water/moisture incursion has been eliminated. On renovation projects, examine walls that are to receive wallcovering and assure they do not exhibit any mold/mildew. All mold and mildew must be removed and surfaces treated to inhibit future growth. In order to reduce the risk of mold/mildew, Koroseal Interior Products, LLC utilized an inhibitor in the wallcovering. The company can also provide a service of microventing the wallcovering whereby more than 25,000 micro-holes /ft2 are fused through the vinyl thereby making it permeable.